



BONDERFLEX 2000 BIANCO E GRIGIO C2TE S1

powder adhesive for laying ceramic tiles in big size

Line

GENERALKOLL

Function

Adhesive in powder for laying ceramic tiles in big size

Materials

Laying of ceramic tiles floors and walls in big size

How to use

Mix 25 kg. of BONDERFLEX 2000 with 6 - 6.5 litres of clean water, possibly using a low-speed mixer, until to obtain a homogeneous mixture without clots. □

Leave the mixture standing about 5-10 minutes then mix again, at least 30 seconds, before using. The prepared mixture, mixed again immediately before using, has a shelf-life of about 1-2 hours (according to environmental conditions: temperature, ventilation, etc.). □

Packaging

multi-layer polythene-lined paper bags. □
Bags of 25 kg. each. Pallets of 1500 kg □

Characteristics

White and grey powder. □

APPLICATION TEMPERATURE □ between 5Â°C and 35Â°C (41Â°F and 95Â°F). □

MIXTURE SHELF-LIFE 1-2 hours □

OPEN TIME â%¥30 minutes □

Important

ALWAYS EFFECT A PRELIMINARY TEST BEFORE THE APPLICATION