



MARMOFLASH

For damp polishing by using traditional or/and single-brush polishing machines

Line

POLISHING POWDERS

Function

Damp polishing of marble

Materials

Marble

How to use

Clean the surface and remove any mechanical residue: nails, brick dust, crushed stone, etc. Apply 30 to 60 grams of product per square meter of surface (1-2 oz/y²), sprinkling the powder over surface; then place the machine's felt pad on top of the powder, dampen area and buff to obtain a milky consistency. Work a few square yards at a time. Buffing will cause the water to evaporate, and the drying marble will be polished. A patina of product will remain on the surface; on a small area use a rag to remove the surface patina and check the level of gloss underneath. Repeat procedure if desired. After completing the polishing phase on the entire surface to be treated, remove the residual patina by washing with Neutrex diluted in a 1:5 water solution. Rinse with clear water. After drying (24 to 48 hours) apply the anti-infiltrant Imperston to preserve the polish and avoid staining from oil, food, etc.

Packaging

Kg 1-5-10

Characteristics

Different components having strong reagent capacity make this classic

Important

ALWAYS EFFECT A PRELIMINARY TEST BEFORE THE APPLICATION